



FIBERS & TEXTILES COMPANY

High-Performance Materials For Your Hardworking Products

420/2 Nylon 66 Tirecord

Properties	Min	Max	Units
Peel Pad Adhesion	20.00		LBS
Dip Pickup	4.00	8.00	%
Elongation at Specified Load	3.50	6.00	%
SQYDW	5.43	5.99	OZ/YD ²
Tensile	15.20		LBS
Shrinkage	0.80	2.50	%
Ultimate Elongation	10.00		%
Width	44.00	45.00	IN
Ends/Inch	46.00	± .5	EPI
Warp Yarn	420 denier N66 2ply		
Fill Yarn	30/1 Cotton		
Shell	5" OD 1 3/8 Square Openings		